



TYPICAL PROPERTIES			
PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE
Melt Flow Rate (230°C/2.16Kg)	ASTM D1238	g/10 min	25.0 ± 3.0
Density	ASTM 1505	g/cm ³	0.9
Colour	ASTM E313	Yi	0 max
Tensile Yield Strength (50mm/min)	ASTM D638	MPa	35
Yield Elongation (50mm/min)	ASTM D638	%	10
Tensile at break (50mm/min)	ASTM D638	MPa	34
Elongation at break (50mm/min)	ASTM D638	%	20
Flexural Modulus at 1.3mm/min (1% sec)	ASTM D790	MPa	1550
Notched Izod Impact Strength at 23°C	ASTM D256-A	455 kPa	38
		1820 kPa	55
Heat Deflection Temperature	ASTM D648	° C	108
			55

Typical data not to be used as specifications

Polypropylene **HD10XS** is a narrow molecular weight distribution polypropylene homopolymer and is formulated with an anti-gasfading stabilization package.

APPLICATIONS

Spunbond, fine fibres, continuous filaments

The technical information provided by Polychim Industrie S.A.S. herein is presented in good faith, to the best of our knowledge and based on information we believe is reliable. However no warranty of merchantability or fitness for a particular purpose is implied or expressed for present or future as Polychim Industrie S.A.S reserves the right to change the composition of its products in order to enhance merchantability and/or performance. Nor will Polychim Industrie S.A.S be liable for any direct, indirect, special, incidental, or consequential loss or damage, regardless of legal theory, negligence or strict liability. It is the customer's responsibility to inspect and to test our products in order to satisfy themselves as to the suitability of the products to their particular purpose. The customer is responsible for the appropriate, safe and legal use, processing and handling our products.

